

SC803

Dimensioneringstabeller

02.8.2019

Öppna profiler pelare R30

F/A (m-1)	Torrfilm i mm för resp. kritisk ståltemperatur																	
	350°C	g/m ²	400°C	g/m ²	450°C	g/m ²	500°C	g/m ²	550°C	g/m ²	600°C	g/m ²	650°C	g/m ²	700°C	g/m ²	750°C	g/m ²
μ ₀					> 90%		~79%		~61%		~45%		~33%		~24%		~18%	
340	0,986	1972	0,612	1225	0,425	849	0,350	700	0,230	460	0,226	452	0,226	452	0,226	452	0,226	452
345	1,005	2009	0,630	1259	0,429	859	0,355	709	0,236	472	0,226	452	0,226	452	0,226	452	0,226	452
350	1,023	2046	0,647	1294	0,434	868	0,359	718	0,243	485	0,226	452	0,226	452	0,226	452	0,226	452
355	1,042	2084	0,664	1328	0,439	877	0,364	728	0,249	498	0,226	452	0,226	452	0,226	452	0,226	452
360	1,061	2121	0,681	1363	0,443	887	0,368	737	0,256	511	0,226	452	0,226	452	0,226	452	0,226	452
365	1,079	2159	0,699	1397	0,448	896	0,373	746	0,262	524	0,226	452	0,226	452	0,226	452	0,226	452
370	1,098	2196	0,716	1432	0,453	905	0,378	756	0,268	537	0,226	452	0,226	452	0,226	452	0,226	452
375	1,117	2233	0,733	1466	0,457	915	0,382	765	0,275	550	0,226	452	0,226	452	0,226	452	0,226	452
380	1,135	2271	0,750	1501	0,462	924	0,387	774	0,281	563	0,226	452	0,226	452	0,226	452	0,226	452
385	1,154	2308	0,768	1535	0,467	934	0,392	783	0,288	576	0,226	452	0,226	452	0,226	452	0,226	452
390	1,173	2346	0,785	1570	0,471	943	0,396	793	0,294	589	0,227	455	0,226	452	0,226	452	0,226	452
395	1,191	2383	0,802	1604	0,476	952	0,401	802	0,301	601	0,233	466	0,226	452	0,226	452	0,226	452
400	1,210	2420	0,820	1639	0,481	962	0,406	811	0,307	614	0,238	476	0,226	452	0,226	452	0,226	452
405	1,229	2458	0,838	1676	0,485	971	0,410	820	0,314	627	0,244	487	0,226	452	0,226	452	0,226	452

SC803

Dimensioneringstabeller

02.8.2019

Öppna profiler pelare R60

F/A (m ⁻¹)	Torrfilm i mm för resp. kritisk ståltemperatur																	
	350°C	g/m ²	400°C	g/m ²	450°C	g/m ²	500°C	g/m ²	550°C	g/m ²	600°C	g/m ²	650°C	g/m ²	700°C	g/m ²	750°C	g/m ²
μ ₀					> 90%		~79%		~61%		~45%		~33%		~24%		~18%	
340	-		-		-		1,318	2636	0,852	1703	0,758	1516	0,673	1346	0,466	931	0,404	808
345	-		-		-		1,354	2708	0,887	1774	0,765	1530	0,680	1361	0,471	941	0,408	816
350	-		-		-		1,390	2780	0,923	1845	0,772	1543	0,688	1375	0,476	951	0,412	824
355	-		-		-		1,426	2852	0,958	1916	0,779	1557	0,695	1390	0,481	961	0,416	832
360	-		-		-		1,462	2924	0,994	1987	0,786	1571	0,702	1405	0,486	971	0,420	840
365	-		-		-		1,498	2997	1,029	2058	0,793	1585	0,710	1419	0,491	981	0,424	848
370	-		-		-		1,534	3069	1,064	2129	0,800	1599	0,717	1434	0,496	991	0,428	856
375	-		-		-		1,571	3141	1,100	2200	0,807	1613	0,724	1449	0,501	1001	0,432	865
380	-		-		-		1,607	3213	1,135	2271	0,814	1627	0,732	1463	0,506	1011	0,436	873
385	-		-		-		-		1,171	2342	0,820	1641	0,739	1478	0,511	1021	0,440	881
390	-		-		-		-		1,206	2413	0,829	1658	0,746	1493	0,522	1044	0,444	889
395	-		-		-		-		1,244	2489	0,861	1722	0,754	1507	0,536	1073	0,449	897
400	-		-		-		-		1,312	2624	0,893	1787	0,761	1522	0,550	1101	0,453	905
405	-		-		-		-		1,379	2759	0,926	1851	0,768	1537	0,565	1129	0,457	913

SC803

Dimensioneringstabeller

02.8.2019

Öppna profiler pelare R90

F/A (m-1)	Torrfilm i mm för resp. kritisk ståltemperatur																		
	350°C	g/m ²	400°C	g/m ²	450°C	g/m ²	500°C	g/m ²	550°C	g/m ²	600°C	g/m ²	650°C	g/m ²	700°C	g/m ²	750°C	g/m ²	
μ ₀					> 90%				~79%				~45%				~24%		~18%
340	-		-		-		-		-		-		-		1,087	2173	0,966	1932	
345	-		-		-		-		-		-		-		1,127	2253	0,986	1971	
350	-		-		-		-		-		-		-		1,166	2333	1,005	2010	
355	-		-		-		-		-		-		-		1,206	2412	1,024	2049	
360	-		-		-		-		-		-		-		1,255	2510	1,044	2088	
365	-		-		-		-		-		-		-		1,344	2688	1,063	2127	
370	-		-		-		-		-		-		-		1,433	2865	1,083	2166	
375	-		-		-		-		-		-		-		1,522	3043	1,102	2205	
380	-		-		-		-		-		-		-		-		1,122	2244	
385	-		-		-		-		-		-		-		-		1,141	2283	
390	-		-		-		-		-		-		-		-		1,161	2322	
395	-		-		-		-		-		-		-		-		1,180	2361	
400	-		-		-		-		-		-		-		-		1,200	2400	
405	-		-		-		-		-		-		-		-		1,219	2439	

SC803

Dimensioneringstabeller



02.8.2019

Slutna profiler R30																				
F/A (m-1)	Torrfilm i mm för resp. kritisk ståltemperatur																			
	350°C	g/m ²	400°C	g/m ²	450°C	g/m ²	500°C	g/m ²	520°C	g/m ²	550°C	g/m ²	600°C	g/m ²	650°C	g/m ²	700°C	g/m ²	750°C	g/m ²
μ ₀					> 90%		~79%		~72%		~61%		~45%		~33%		~24%		~18%	
340	2,849	5698	2,532	5065	2,290	4580	1,970	3940	1,837	3675	1,631	3262	1,183	2366	0,571	1143	0,262	525	0,175	350
345	2,883	5765	2,572	5145	2,330	4660	2,007	4015	1,874	3747	1,663	3326	1,232	2465	0,602	1204	0,284	567	0,175	350
350	2,916	5833	2,613	5225	2,371	4741	2,045	4090	1,910	3819	1,695	3391	1,282	2564	0,633	1265	0,305	609	0,175	350
355	2,950	5900	2,653	5305	2,411	4822	2,082	4165	1,946	3891	1,728	3456	1,331	2663	0,663	1327	0,326	652	0,175	350
360	2,984	5968	2,693	5385	2,451	4902	2,120	4239	1,982	3963	1,760	3520	1,381	2762	0,694	1388	0,347	694	0,175	350
365	3,018	6035	2,733	5465	2,492	4983	2,157	4314	2,018	4035	1,792	3585	1,431	2861	0,725	1449	0,368	736	0,175	350
370	3,051	6102	2,773	5546	2,532	5064	2,195	4389	2,054	4107	1,825	3650	1,477	2953	0,755	1510	0,389	779	0,175	350
375	3,085	6170	2,806	5613	2,572	5144	2,232	4464	2,090	4179	1,857	3714	1,505	3010	0,786	1572	0,411	821	0,175	350
380	3,119	6237	2,840	5680	2,613	5225	2,269	4539	2,126	4251	1,889	3779	1,534	3067	0,817	1633	0,432	863	0,175	350
385	3,152	6305	2,874	5747	2,653	5306	2,307	4614	2,162	4323	1,922	3844	1,562	3125	0,847	1694	0,453	906	0,175	350
390	3,186	6372	2,907	5815	2,693	5386	2,344	4689	2,198	4395	1,954	3908	1,591	3182	0,878	1756	0,474	948	0,175	350
395	3,220	6439	2,941	5882	2,734	5467	2,382	4763	2,234	4468	1,986	3973	1,619	3239	0,909	1817	0,495	990	0,175	350
400	3,253	6507	2,975	5949	2,774	5547	2,419	4838	2,270	4540	2,019	4038	1,648	3296	0,961	1923	0,516	1033	0,175	350
405	3,287	6574	3,008	6016	2,803	5605	2,457	4913	2,306	4612	2,051	4102	1,676	3353	1,019	2038	0,537	1075	0,182	363
410	3,321	6642	3,042	6084	2,832	5663	2,494	4988	2,342	4684	2,083	4167	1,705	3410	1,077	2153	0,559	1117	0,195	389
415	3,355	6709	3,075	6151	2,861	5721	2,531	5063	2,378	4756	2,116	4232	1,734	3467	1,134	2268	0,580	1160	0,208	416

SC803

Dimensioneringstabeller



02.8.2019

Slutna profiler R60

F/A (m-1)	Torrfilm i mm för resp. kritisk ståltemperatur																			
	350°C	g/m ²	400°C	g/m ²	450°C	g/m ²	500°C	g/m ²	520°C	g/m ²	550°C	g/m ²	600°C	g/m ²	650°C	g/m ²	700°C	g/m ²	750°C	g/m ²
μ ₀					> 90%		~79%		~72%		~61%		~45%		~33%		~24%		~18%	
340	-		-		-		-		-		-		3,726	7452	3,295	6590	2,742	5485	2,206	4411
345	-		-		-		-		-		-		3,791	7581	3,359	6719	2,797	5594	2,250	4500
350	-		-		-		-		-		-		3,855	7710	3,424	6848	2,858	5717	2,294	4589
355	-		-		-		-		-		-		3,920	7839	3,488	6977	2,920	5840	2,339	4678
360	-		-		-		-		-		-		3,984	7968	3,553	7106	2,981	5962	2,383	4767
365	-		-		-		-		-		-		4,049	8098	3,617	7234	3,042	6085	2,428	4855
370	-		-		-		-		-		-		4,113	8227	3,682	7363	3,104	6208	2,472	4944
375	-		-		-		-		-		-		-		3,746	7492	3,165	6330	2,517	5033
380	-		-		-		-		-		-		-		3,811	7621	3,227	6453	2,561	5122
385	-		-		-		-		-		-		-		3,875	7750	3,288	6576	2,605	5211
390	-		-		-		-		-		-		-		3,939	7879	3,349	6699	2,650	5300
395	-		-		-		-		-		-		-		4,004	8008	3,411	6821	2,694	5389
400	-		-		-		-		-		-		-		4,068	8137	3,472	6944	2,739	5477
405	-		-		-		-		-		-		-		-		3,533	7067	2,785	5570
410	-		-		-		-		-		-		-		-		3,595	7190	2,839	5678
415	-		-		-		-		-		-		-		-		3,656	7312	2,892	5785

