

NTN 005

Surface Salt Contamination Levels

Nullifire
Smart Protection

Recommendations

The follow are Tremco CPG UK's guidelines for the allowable level of surface salt contamination on the substrate prior to coating.

- For **exposed coastal or marine** environments a maximum surface salt level of **7µg/cm²**
- For **inland rural or industrial** atmospheric exposure, a maximum surface salt level of **10µg/cm²**

Please note that this is an opinion only and we reserve the right to amend these levels if certain circumstances dictated this.

Technical Service

Nullifire has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Technical Services on 01942 251400.