

NTN 052

Over Coating FS702 Intumastic

Nullifire
Smart Protection

Over Coating FS702 Intumastic

FS702 Intumastic (once fully cured) may be over coated with any standard trade emulsion or gloss in order to achieve a specific colour.

Care should be taken to ensure the surface is free from dust and grease that may be settled during the curing process before over coating commences.

FS702 Intumastic may be lightly sanded and filled using proprietary fillers without negating its fire performance.

Always follow the paint manufacturers instructions: FS702 Intumastic is an acrylic product not a gypsum based product, some paint manufacturers request a primer layer before application of top coat.

For specialist paints (chlorinated rubbers and alike) Nullifire technical, will require data sheets to be presented so as to confirm compatibility.

If the area in which the surface is to be painted requires a maximum spread of flame (Class 0) for example, great care should be taken to select a correctly conformant top coat. Always follow the paint manufacturers recommendation and guidelines.

FS702 Intumastic will absorb paint readily, more coats than expected will be required in order to achieve your RAL colour.

This becomes extremely noticeable on dark colours.

If paint surfaces cracks the indicators are to poor preparation, insufficient curing time or an incompatible top coat: always carry out a sample area before commencing with your project.

Gypsum or cement based self-levelling waterproof screeds, will have no adverse effect on the fire performance of FS702 Intumastic.

Both the FS702 Intumastic and the top coat/screed must be strictly applied in full accordance to the manufacturers data sheets.

Technical Service

Nullifire have a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, on technical advise, please call our technical hub on 01942 251400